


No. : TJIN2004003592MR

Date : Apr 28, 2020





CUSTOMER NAME:	CHANGSHU STP NEW MATERIAL CO., LTD.	0.00000
ADDRESS:	#88 HAIFENG ROAD, HAIYU TOWN, CHANGSHU CITY, JIAN	JSU
	PROVINCE, CHINA.	
Sample Name :	FLAME RETARDANT SILICONE RUBBER COATED FIBER	≷GLASS
	CLOTH	

Product Specification	:	0.5mm
Manufacturer	:	CHANGSHU STP NEW MATERIAL CO., LTD.
Material and Mark	:	SILICONE RUBBER
Other Information	:	SILICONE RUBBER、FIBERGLASS

Above information and sample(s) was/were submitted and confirmed by the client. SGS, however, assumes no responsibility to verify the accuracy, adequacy and completeness of the sample information provided by client.

SGS Ref. No.	:	TP20-002196-2
Date of Receipt	:	Apr 15, 2020
Testing Start Date	:	Apr 15, 2020
Testing End Date	:	Apr 28, 2020
Test result(s)	:	For further details, please refer to the following page(s) (Unless otherwise stated the results shown in this test report refer only to the sample(s) tested)

Signed for SGS-CSTC Standards Technical Services(Tianjin) Co., Ltd

Linda Yuan Authorized signatory



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.ags.com/en/Terms-and-Conditions.agx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <u>http://www.sgs.com/en/Terms-and-Conditions/Terms-en-Document.agx</u>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the lime of its intervention only and within the limits of Cilent's instructions, if any. The Company's soft esponsibility is to its Cilent and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or faisification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only. Attention:To check the authenticity of testing / inspection report & certificate, please contact us at telephone:(86-755) 8307 1443, or email: CN.Doccheck@ags.com

 Building C-13, No.80, Haiyun Avenue, TEDA, Tianjin, China 300457
 t
 (86-22)
 5999
 5319
 f
 (86-22)
 5999
 5335
 www.sgsgroup.com.cn

 中国・天津・经济技术开发区海云街80号C-13厂房
 卸编: 300457
 t
 (86-22)
 5999
 5319
 f
 (86-22)
 5999
 5335
 e
 sgs.china@sgs.com



No. : TJIN2004003592MR Date : Apr 28, 2020 Page: 2 of 6

Summary of Results:


No.	Test Item	Test Method	Result	Conclusion
1	Vertical Burning	UL 94-2013 Rev.9-2018 Section 8	V-0	/

Note: Pass : Meet the requirements;

Fail : Does not meet the requirements;

/: Not Apply to the judgment.

Original Sample Photo:





Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-en-Document.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained herein reflects the Company's findings at the time of its intervention only and within the limits of Cilent's instructions, if any. The Company's sole responsibility is to its Cilent and this document cannot be reproduced except in fill, without prior written approval of the Company. Any unauthorized alteration, forger or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only. Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone:(86-755) 8307 1443. or email: CN_Docheck@ass.com

Building C-13, No.80, Halyun Avenue, TEDA, Tianjin, China 300457 t(86-22)5999 5319 f(86-22)5999 5335 www.sgsgroup.com.cn 中国・天津・经济技术开发区海云街80号C-13厂房 邮编:300457 t(86-22)5999 5319 f(86-22)5999 5335 e sgs.china@sgs.com



No. : TJIN2004003592MR Date : Apr 28, 2020 Page: 3 of 6

Test Item: Vertical Burning

Sample Description: Rubber part

Test Method: UL 94-2013 Rev.9-2018 Section 8

Test Condition:

Specimen: 124mm×13mm×0.45mm

Test Result:

Conditioning	As received :(23±2)℃, (50±5)%RH, 48h		Ageing: (70±2)℃, 168h→ Desiccator, (23±2)℃, 4h							
Specimen	1	2	3	4	5	1	2	3	4	5
Afterflame time after the first flame application (s), t ₁	6.4	7.2	5.6	8.9	4.7	5.2	4.3	6.5	5.9	7.1
Afterflame time after the second flame application (s), t ₂	1.4	2.1	3.2	1.7	5.6	2.4	3.9	2.7	5.7	3.3
Afterglow time after the second application (s), t ₃	0	0	0	0	0	0	0	0	0	0
Total afterflame time for any condition set (s), t ₁ +t ₂	46.8		47.0							
Afterflame time plus afterglow time after the second flame application (s), t_2+t_3	1.4	2.1	3.2	1.7	5.6	2.4	3.9	2.7	5.7	3.3
Whether or not specimen burn up to the holding clamp	No	No	No	No	No	No	No	No	No	No
Whether or not the cotton was ignited by flaming particles or drops	No	No	No	No	No	No	No	No	No	No



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.asp and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <a href="http://www.sgs.com/en/Terms-and-Conditions/Terms-and-Condit

Building C-13, No.80, Haiyun Avenue, TEDA, Tianjin, China 300457 t(86-22)5999 5319 f(86-22)5999 5335 www.sgsgroup.com.cn 中国・天津・经济技术开发区落云街80号C-13厂房 邮编: 300457 t(86-22)5999 5319 f(86-22)5999 5335 e sgs.china@sgs.com



No. : TJIN2004003592MR Date : Apr 28, 2020 Page: 4 of 6

Classification: V-0 (See table 1)

Table 1

Criteria conditions	V-0	V-1	V-2
Afterflame time for each individual specimen t1 or t2	≪10s	≪30s	≪30s
Total afterflame time for any condition set (t ₁ plus t ₂ for the 5 specimens)	≪50s	≪250s	≤250s
Afterflame plus afterglow time for each individual specimen after the second flame application (t ₂ +t ₃)	≪30s	≪60s	≪60s
Afterflame or afterglow of any specimen up to the holding clamp	No	No	No
Cotton indicator ignited by flaming particles or drops	No	No	Yes



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.apx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-en-Document.aspx. Attention is drawn to the limitation of liability, indermification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Cilent's instructions, if any. The Company's soft esponsibility is to its Cilent and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document to approval of the Company. Any unauthorized alteration, forgery or faisification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) itested and such sample(s) are retained for 30 days only. Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone:(86-755) 8307 1443, or email: CN_Docheck@ass.com


 Building C-13, No.80, Haiyun Avenue, TEDA, Tianjin, China 300457
 t
 (86-22)
 5999
 5319
 f
 (86-22)
 5999
 5335
 www.sgsgroup.com.cn

 中国・天津・经济技术开发区海云街80号C-13厂房
 邮编: 300457
 t
 (86-22)
 5999
 5319
 f
 (86-22)
 5999
 5335
 e
 sgs.china@sgs.com



No. : TJIN2004003592MR Date : Apr 28, 2020 Page: 5 of 6

Test Photo:





Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.asp and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <a href="http://www.sgs.com/en/Terms-and-Conditions/Terms-and-Condit

Building C-13, No.80, Haiyun Avenue, TEDA, Tianjin, China 300457 t (86-22) 5999 5319 f (86-22) 5999 5335 www.sgsgroup.com.cn 中国・天津・经济技术开发区海云街80号C-13厂房 卸编: 300457 t (86-22) 5999 5319 f (86-22) 5999 5335 e sgs.china@sgs.com



No. : TJIN2004003592MR Date : Apr 28, 2020 Page: 6 of 6

Equipment Information:

Equipment	Model	Equipment No.	Calibration date	Next Calibration date
Digital Thickness Gauge	TG-3130-A3	POL-127	2019-11-01	2020-10-31
Horizontal/Vertical Flame Chamber	HVUL2	POL-241	2019-09-26	2020-09-25

Unless otherwise stated, the results show in this test report refer only to sample(s) tested; test report shall only be used for clients' scientific research, teaching, internal quality control, product research and development, etc... and just for internal reference. Without written approval or consent of our company, the test result shall not be used for improper publicity.

******** End of report*******



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <u>http://www.sgs.com/en/Terms-and-Conditions.aspx</u> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <u>http://www.sgs.com/en/Terms-and-Conditions.aspx</u> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <u>http://www.sgs.com/en/Terms-and-Conditions.aspx</u> and, for electronic format documents, advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits to Cilent's instructions, if any. The Company's sole responsibility is to its Cilent and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in fill, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only. Attention:To check the authenticity of testing / inspection report & certificate, please contact us at telephone:(86-755) 8307 1443. or remail: CN Docheck/Mass com

Building C-13, No.80, Haiyun Avenue, TEDA, Tianjin, China 300457 t(86-22)5999 5319 f(86-22)5999 5335 www.sgsgroup.com.cn 中国・天津・经济技术开发区海云街80号C-13厂房 邮编:300457 t(86-22)5999 5319 f(86-22)5999 5335 e sgs.china@sgs.com